

Pre-Measured Epoxy Patch Kit 400

FEATURES

- 100% Epoxy Resin Base with a Catalyst hardener and special blended aggregate
- 18,000 psi compression strength
- Will not break down at temperatures below 550° F
- Withstands heavy, abusive traffic
- Absorbs vibration and shock without cracking
- Excellent for expansion and contraction applications
- Highly resistant to acids, alkalies, solvents, heat and cold
- Extra-long wearing – permanent and resilient
- Self-leveling – minimal trowel work
- Bonds to concrete, steel and wood
- Kit covers 15-18 sq. ft. at 1/4 " thick

HOW TO USE

1. Ready floor by removing all loose material. Sweep away dirt. Degrease areas which have a thick build-up of grease with 207
2. Remove the cradle which contains Part B (pint) and 10 lbs. special aggregate.
3. Thoroughly mix Part A (which contains 12 lbs. special aggregate) until uniform.
4. Pour entire contents of Part (B) into Part (A), which is in the bottom of the pail. Mix Parts A & B for 2-3 minutes.
5. Add special aggregate from cradle to mixed Parts (A & B) to desired consistency, thick for troweling, thin for pouring.
6. Fill holes, cracks, crevices to level of existing floor. Feather edges with a trowel. Wet trowel with epoxy thinner and finish off to a smooth surface.

NOTE: You have 25-30 minutes to apply product to floor. 400 dries in 12-18 hours for light traffic and 48-72 hours for heavy traffic. Each kit covers 15-18 sq. ft. at 1/4" thickness.

SPECIFICATIONS

	Part A	Part B	Part C
Physical Form	viscous liquid	liquid hardener	granules
Color	clear	clear to light amber	sand
Odor	acrylate	amine	n/a
Specific Gravity	1.13	1.0	70 lb./ft.
Flash Point (TCC)	200+°F	200+°F	None