

TECHNICAL DATA SHEET

Chemical Resistant Epoxy Patch 403HP

FEATURES

- Cures on damp concrete; however, standing water must be removed
- 100% Epoxy Resin Base with a Catalyst hardener and special blended aggregate
- 15,500 psi compression strength
- Can be exposed to temperatures up to 250°F and a variety of chemicals such as hot oil and grease
- Withstands heavy, abusive traffic
- Absorbs vibration and shock without cracking
- Cures down to 32°F
- 25 hour cure
- Pot life of 90 minutes at 70-75°F in a 5 oz. mass.
- Excellent for expansion and contraction applications
- Highly resistant to acids, alkalies, solvents, heat and cold

Part A

- Extra-long wearing permanent and resilient
- Self-leveling minimal trowel work
- Bonds to concrete, steel and wood
- Available in clear, white, black, red, blue, orange, purple, yellow, green, gray, tan
- Single kit covers 22-24 sq. ft. at ⅓" thick (1/2 gallon part A, 1 quart part B, 42 lbs. aggregate)

HOW TO USE

Ready floor by removing all loose materials. To assure a clean, sound surface prior to patching, clean heavy deposits of oil and grease with 217 for heavy incrustations of oil and grease. Pour two Parts A into one Part B and mix for approximately 1 ½ -2 minutes. Add Part C slowly while continuing to stir until desired consistency is achieved.

Part R

Part C

SPECIFICATIONS

	I WILL	i di C D	i di C
Physical Form	viscous liquid	Liquid hardener	Granules
Color	pigmented	clear	Gray
Odor	acrylate	amine	n/a
Specific Gravity	1.13	1.0	70 lb/ft
Flash Point (TCC)	200+°F	200+°F	none