



TECHNICAL DATA

POLYASPARTIC TOP COAT

90% SOLIDS, LOW ODOR POLYASPARTIC PRIMER, BODY AND FINISH COATING

DESCRIPTION:

POLYASPARTIC TOP COAT is a water clear, 2-component, 90% solids modified aliphatic / polyaspartic coating that combines the best attributes of high grade epoxy and urethane coatings. **POLYASPARTIC TOP COAT** offers the highest UV resistance available, remains flexible over time and has very good abrasion and chemical resistance. **POLYASPARTIC TOP COAT** has zero reportable VOCs, zero HAPS and meets all USDA/FDA guidelines for use in federally inspected facilities.

USES and TYPICAL COVERAGE:

As a BODY or FINISH coat: **POLYASPARTIC TOP COAT** is an excellent non-yellowing, body or finish coat for any SUPERIOR floor or wall coating system. This coating is recommended for use in moderate temperature environments (40°-70°F) that require fast return to service and/or superior UV resistance while maintaining VOC compliance. Typical coverage per coat is from 80 sq. ft. /gal. (20 mils) to 150 sq. ft. / gal. (11 mils). For a lower viscosity you may add up to 16 oz. Viscosity Reducer per mixed gallon of **POLYASPARTIC TOP COAT**.

ADVANTAGES:

As a PRIMER coat: **POLYASPARTIC TOP COAT** can be used as a fast setting, water clear primer by adding P100 V.2014 Viscosity Reducer at 10 oz. per mixed gallon of P100. Coverage will increase to 200+ sq. ft. / gal. (8+ mils).

- Water clear and Superior UV resistance
- Very Good chemical and abrasion resistance
- Low Odor even with Viscosity Reducer added
- Viscosity can be changed in the field per the job needs
- Single coat high build capabilities – apply at up to 20 mils per coat
- Zero reportable HAPS / VOCs even with Viscosity Reducer
- Easy working formula for installations between 40°- 70°F
- Can be tinted with SUPERIOR Universal Colorants EXCEPT VELVET and LIGHT BLUE. Loading is one 1.5 Colorant Jar (1/2 BagPak of Colorant) per 3 gallon mix

TYPICAL PROPERTIES:

PHYSICAL PROPERTIES	
Volume mix ratio	2 to 1 (Resin to Hardener)
Viscosity (mixed)	650 CPS Typical
Solids Content (%)	90% (ASTM D-2697)
Hardness (ASTM D-2440)	55-60 (Shore D) @ 7 day cure
VOC	0.8 g/l (EPA method 24)
Application Temps.	40° – 70° F
Gel Time (see "Limitations" section below for more details)	60 minutes @ 75°F
Dry to Touch (recoat with compatible products)	1 hour @ 75°F
Through Cure	3.5 hours @ 75°F
Open for light traffic/use	24 hours @ 75°F
Shelf Life	1 Year in unopened units

PACKAGING:

- 3.0 Gallon Units
- 15 Gallon Units

TECH DATA SHEET POLYASPARTIC TOP COAT

POLYASPARTIC TOP COAT

LIMITATIONS & FOR BEST RESULTS:

- May be thinned with up to 16 oz. Viscosity Reducer per mixed gallon of Polyaspartic Top Coat. When using as primer use a minimum of 10 oz. of Viscosity Reducer per mixed gallon of Polyaspartic Top Coat. *Adding Viscosity Reducer will lower the viscosity and slightly increase the odor during cure, but will not alter the reportable VOC content. Adding Viscosity Reducer will slow the cure time, but will not change the performance characteristics of the cured material.*
- Do not apply when humidity exceeds 70%.
- Do not allow to puddle during application.
- Allow each coat to dry to 'tack-free' or clear prior to re-coat.
- When re-coating, apply the next coat within 24 hours of completing the previous coat.
- Mix on very low RPM or using a stir stick for 45-60 seconds. **DO NOT INTRODUCE ANY AIR.**
- When possible, squeegee on the shorter length of the room and immediately back roll in one pass in the opposite direction to strike off. Thickness of application should be controlled by the squeegee. Do not rely on back roll to eliminate puddles. Do not over back-roll as this will entrain air.
- Gel time listed above for this product should not be confused with working time – actual working time is typically 8-10 minutes at 70°F and 45% RH when no Viscosity Reducer has been added.

PRODUCT APPLICATION:

Apply by brush, roller and squeegee. 12" squeegees are recommended to help reduce pooling. Unlike epoxy coatings Polyaspartic Top Coat has a longer "pot life" in the bucket and a shorter working time after it is poured onto the substrate. For best results installation crews must work closely together and pour out only enough catalyzed material that can be cut in, squeegeed and quickly back rolled before it starts to gel. Temperature and humidity will both increase how rapidly this material sets. When working on warmer or more humid job sites smaller mixes thinned with the maximum amount of Viscosity Reducer are recommended. SUPERIOR product test data is based on environmental temperatures of 75°F. Viscosity and working time are always affected by temperatures above or below that mark. When applying product – always consider the ambient, surface, and product temperature at the time and place of installation.

COLOR AND TEXTURES:

POLYASPARTIC TOP COAT is manufactured in water clear. Using a 1.5 Jar (equal to 1/2 of one Colorant BagPak) of SUPERIOR UNIVERSAL Colorant per 3.0 gallon mix is acceptable except for VELVET or LIGHT BLUE – do not use VELVET or LIGHT BLUE with this product. Most SUPERIOR products are available in a wide range of textures using an appropriate aggregate.

PRODUCT STORAGE:

DO NOT allow SUPERIOR products to freeze. All SUPERIOR products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50° F.

CHEMICAL RESISTANCE:

Always refer to SUPERIOR's chemical resistance chart for specific information on each product / system or contact SUPERIOR directly.

SURFACE PREPARATION: Always apply SUPERIOR products to a clean / sound substrate that is free of laitance, grease, oils, debris, and curing compounds. Concrete substrates should be cured for a minimum of 28 days prior to application of product [except as otherwise noted on the individual Product Data Sheet. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is not possible always perform tests to

determine adhesion and compatibility to the existing flooring. Mechanical preparation by means of a diamond grinding or shot-blasting machine to a minimum CSP-2 profile followed by application of **POLYASPARTIC TOP COAT** at least 10 oz. of Viscosity Reducer per gallon, or another appropriate SUPERIOR primer or base system is the best and recommended installation method for **POLYASPARTIC TOP COAT** applications. If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

CLEAN UP:

Application tools and equipment can be cleaned with soap and water immediately after use or with solvent once the product has begun to cure.

DISPOSAL:

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

IMPORTANT NOTICE:

Always read and acquaint yourself with SUPERIOR's Product Data Sheet, SDS [safety data sheet], and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions – contact your Area Sales Representative or SUPERIOR directly for recommendations. Kit components are pre-measured for optimal performance. Catalyzed errors due to incorrect mixing in the field voids product warranty.

WARRANTY: Information about SUPERIOR products is given, to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you make your own tests to determine suitability of the product for the particular purpose. As products are often applied or used under conditions beyond our control, SUPERIOR cannot guarantee anything except the quality of its products. SUPERIOR warrants that the products meet the specifications set forth by SUPERIOR, but we reserve the right to change any given specification prior to notice. SUPERIOR DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of a SUPERIOR product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of the merchandise, purchaser has 30 days to notify SUPERIOR, in writing, that materials are defective. In the event SUPERIOR finds that the product delivered is off specification, SUPERIOR will, at its sole discretion, either replace the product(s) or refund the purchase price thereof, and SUPERIOR's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of SUPERIOR exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. SUPERIOR will, under no circumstance, be liable for special, incidental, or consequential damages. This warranty supersedes all other guarantees, whether oral or written, and whether expressed, implied, or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Safety Data Sheet and follow all precautions to prevent bodily harm.