

PRODUCT DESCRIPTION

RQP is a multi-purpose 100% solids epoxy repair paste for fast-track repairs and an excellent adhesive for flooring accessory installations. RQP is a two component thixotropic compound that is easily applied directly from the Dual Cartridge Kit, or using a putty knife, trowel or plastic applicator out of bulk kits.

USES

RQP's easy workability and rapid cure time make it an ideal product for last minute "touch ups" to missed pop-outs or small cracks in a substrate prior to applying a coating system. RQP is used to repair chips, defects, small voids or "honeycombing" in horizontal, vertical and overhead concrete substrates. RQP's excellent bond strength, thick consistency and quick setting attributes make it an ideal adhesive to use when setting pre-formed "speed cove", terrazzo strips or termination caps. RQP can be sanded immediately after cure and is strong enough to be drilled, tapped or shaped as needed to conform to the substrate being repaired.

ADVANTAGES

- VOC compliant
- Easy 1:1 mix ratio
- Non-shrink
- Easy application
- Good working time, but fast cure time
- High bond strength and tensile strength

COLORS AND TEXTURES

RQP is only available in gray. The resin component is BLACK and the hardener is WHITE so when mixed properly a uniform gray color is achieved.

PACKAGING

Supplied in complete A+B 2 gallon (7.57 L).
Mix ratio 1A : 1B

TYPICAL COVERAGE

RQP can be applied to a "feather edge" as thin as a blade can strike it off and to nearly infinite depth. Ideally, RQP is applied in lifts less than 3/8" and not over areas more than 2 times wider than the repair depth. Deeper fill repairs may require two or more lifts allowing for cure in between applications.

TECHNICAL DATA

Mixing Ratio by Volume	1A : 1B
Viscosity (mixed)	125,000 CPS
VOC (when mixed as intended)	<50 g/L
Solids Content, by Volume	100%
Hardness (ASTM D-2240)	85 (Shore D)
Application Temps.	50° – 80° F
Gel Time @ 75° F	15 minutes
Dry to Touch (recoat with similar product) @ 75° F	30 minutes
Through Cure @ 75° F (able to sand)	45 minutes

Higher temperatures reduce cure time, lower temperatures increase cure time.

SURFACE PREPARATION

Always apply ROCK-TRED products to a clean / sound substrate that is free of laitance, grease, oils, debris, and curing compounds. Concrete substrates should be cured for a minimum of 28 days prior to application of product [except as otherwise noted on the individual Product Data Sheet]. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is not possible always perform tests to determine adhesion and compatibility to the existing flooring. Mechanical surface preparation to a CSP-2 minimum profile by means of a diamond grinding machine is the best and recommended preparation method for RQP. If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

MIXING

Portion the black colored Part A into a mixing vessel. Portion an equal amount of the white colored Part B into the Part A and mix by hand with a blade, paint stick or power mix with spiral style mixing blade at low speed (300 RPM) for two minutes and until all the material is a solid, homogenous gray color. Do not entrap air during mixing. Avoid mixing and application of RQP if the substrate and/or air temperature are below 50°F or above 85°F, or if the humidity is higher than 75% R.H. The temperature

MIXING (CONT.)

of the substrate, the epoxy, and the air in the area of installation all play a role in cure time (i.e., warmer=faster; cooler=slower). RQP should be tack-free and dry before applying additional coatings. This will vary with temperature and humidity, but is normally between 30 – 45 minutes @ 75°F and 50% R.H.

APPLICATION

Apply by putty knife, trowel or plastic applicator. ROCK-TRED product test data is based on environmental temperatures of 75°F (24°C). Viscosity and working time are always affected by temperatures above or below that mark. When applying product – always consider the ambient, surface, and product temperature at the time and place of installation.

CHEMICAL RESISTANCE

Contact Technical Support for additional information.

PRODUCT STORAGE

DO NOT allow ROCK-TRED products to freeze. All ROCK-TRED products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50°F (10°C).

CLEAN-UP

Application tools and equipment can be cleaned with soap and water immediately after use or with solvent once the product has begun to cure.

DISPOSAL

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

IMPORTANT NOTICE

Always read and acquaint yourself with ROCK-TRED'S Product Data Sheet, SDS [safety data sheet], and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions – contact your local representative or ROCK-TRED directly for recommendations. Catalyzation errors due to incorrect mixing in the field voids product warranty.

LIMITATIONS

- Do not thin this product.
- Do not apply when humidity exceeds 70% indoors.
- Allow each coat to dry to 'tack-free' prior to re-coat.
- When re-coating, always apply the next coat within 24 hours of completing the previous coat.
- Relatively thin applications (¼" width or depth) of RQP are best – avoid deep fill repairs in a single lift as minor cracking during cure may result.
- Mix thoroughly until a uniform gray color is achieved
- Tube Set applicator works best when material is above 65F.

HANDLING & SAFETY

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin; wear protective gloves and safety glasses. User must read and understand Safety Data Sheet before using. ROCK-TRED Safety Data Sheets are available at www.rocktred.com

STANDARD WARRANTY STATEMENT

Rock-Quick Patch PDS 6.18.24

ICP Construction, Inc. ("we" "us" or "our"), manufacturer of Rock-Tred Polymer Coating Solutions, warrants that the product is produced within specifications and is free from defects in material only. No warranty shall be in effect until our Terms and Conditions of Sales (<https://www.icpgroup.com/wp-content/uploads/ICP-Group-Terms-and-Conditions-of-Sale.pdf>) are met, including payment and cooperative promotional considerations. We warrant that the covered product is free of defects in material only and suitable for the specified purpose for a period of one (1) year from the date of shipment, provided the product is (a) installed within its published shelf life, in strict conformance with specifications, and (b) handled, stored, mixed, and applied in accordance with our written instructions. It is your responsibility to initiate any claim against this warranty within the time frame specified below. If we determine that the product meets the requirements of this warranty, then we will, at our sole discretion, either refund the purchase price of the product or provide replacement product, in each case not to exceed the affected area as determined by our authorized technical representative. To obtain replacement or refund you must (a) provide timely written notice to us specifying in detail the non-conformity suspected (no later than five (5) working days after discovery), and (b) provide proof of purchase. We reserve the right to inspect the product prior to replacement. EXCEPT FOR THE EXPRESS WARRANTY ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. IN NO EVENT SHALL WE OR OUR AFFILIATES BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, PUNITIVE, OR CONSEQUENTIAL DAMAGES OF ANY NATURE, REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW, INCLUDING, WITHOUT LIMITATION, BREACH OF ANY OBLIGATION OR WARRANTY IMPOSED ON US HEREUNDER OR IN CONNECTION HERewith, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES IN ADVANCE AND EVEN IF A REMEDY SET FORTH HEREIN IS FOUND TO HAVE FAILED OF ITS ESSENTIAL PURPOSE. "CONSEQUENTIAL DAMAGES" SHALL INCLUDE, WITHOUT LIMITATION, LOSS OF USE, INCOME, OR PROFIT, OR LOSSES SUSTAINED AS THE RESULT OF INJURY TO ANY PERSON, OR LOSS OF OR DAMAGE TO ANY PROPERTY (INCLUDING, WITHOUT LIMITATION, PROPERTY HANDLED OR PROCESSED THROUGH THE USE OF THE PRODUCTS), DAMAGES OR LOSSES RESULTING FROM CLAIMS OF OTHER PERSONS AGAINST YOU, OR DAMAGES OR LOSSES SUSTAINED AS THE RESULT OF WORK STOPPAGE, OR REMOVAL AND REPLACEMENT COSTS AND COSTS OF LABOR. IN NO EVENT SHALL OUR LIABILITY ARISING IN CONNECTION WITH OR UNDER THIS WARRANTY (REGARDLESS OF THE FORM OF ACTION OR THEORY OF LAW) EXCEED THE AMOUNT PAID BY YOU FOR THE DEFECTIVE PRODUCT ONLY. THIS LIMITED WARRANTY PROVIDES YOUR EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT. If you do not agree with these terms, you may return the product within thirty (30) days of purchase for a full refund, provided the product is not opened, altered, or adulterated in any manner, less any shipping and handling charges of any sort. Use of the product, or retention of the product beyond thirty (30) days, constitutes your acceptance of this limited and exclusive warranty. No customer, distributor, or representative of ours is authorized to change or modify the published data sheets or this warranty in any way. No one is authorized to make oral warranties on behalf of us.

